

## Polyester Glitter Grade II

Art.	Partikelgröße / particle size mm	Stärke / thickness mm	Schnitt / cut	Art.	Partikelgröße / particle size mm	Stärke / thickness mm	Schnitt / cut
27201	0,1	0,025 - 0,03	hex	2708	1,6	0,025 - 0,03	hex
2710	0,2	0,025 - 0,03	hex	27085	2,0	0,025 - 0,03	hex
27015	0,3	0,025 - 0,03	hex	2709	2,5	0,025 - 0,03	hex
2701	0,4	0,025 - 0,03	hex	27095	3,0	0,025 - 0,03	hex
2702	0,6	0,025 - 0,03	hex	275020	2,5	0,025 - 0,03	stars
2703	0,8	0,025 - 0,03	hex	275030	3,0	0,025 - 0,03	stars
2704	1,0	0,025 - 0,03	hex	274030	3,0	0,025 - 0,03	hearts
2706	1,3	0,025 - 0,03	hex	277030	3,0	0,025 - 0,03	crescents

Material	Farben / colours	Beständigkeit / resistance				
		Temp.	MEK	low concentrated alcohol	highly concentrated alcohol	H <sub>2</sub> O
Polyester	50-11 02-11 - 118-11	175° 175°	not resistant not resistant	resistant – Please test prior to application.	not resistant not resistant	not resistant resistant – Please test prior to application.
Iridescent	300-11 322-11 324-11	60° 60° 60°	not resistant not resistant not resistant	resistant – Please test prior to application.	not resistant not resistant not resistant	resistant – Please test prior to application.
Iridescent coloured	300FP, FY, FT, FG, FO, FM-11	60°	not resistant	resistant – Please test prior to application.	not resistant	resistant – Please test prior to application.
Hologram	50A-11	175°	not resistant	resistant – Please test prior to application.	resistant – Please test prior to application.	not resistant
	37A-11 - 61A-11	175°	not resistant	resistant – Please test prior to application.	resistant – Please test prior to application.	resistant – Please test prior to application.

MEK 15 min . Isopropanol 15 min . H<sub>2</sub>O 24 Stunden / hours . UV 1 Jahr / 1 year

resistance	test method	product		
		Polyester Glitter Grade I	Polyester Glitter Grade II	Polyester Glitter Grade III
Temperature	laboratory furnace	between 81° C and 175° C	between 60° C and 175° C	between 60° C and 175° C
MEK (Methyl Ethyl Keton)	15 min	resistant	not resistant	not resistant
low concentrated alcohol (30 %)	Isopropanol 15 min	resistant	resistant Please test prior to application.	resistant Please test prior to application.
highly concentrated alcohol (70 %)	Isopropanol 15 min	resistant Please test prior to application.	depends on the raw material used	depends on the raw material used
H <sub>2</sub> O	24 hour	resistant	depends on the raw material used	depends on the raw material used